

**Product Code** EFOX30

**Description** Tert-Butyl Peroxybenzoate

**Specifications;**

Density (@20°C) : 0,810 gr/cm<sup>3</sup>  
Appearance : Colorless, Liquid  
Viscosity (@20°C) : 6,55 mPa.s  
Active Oxygen Content : 8,08%  
Peroxide Content : min. 98%  
SADT : 60°C  
CAS Nr : 614-45-9  
UN Nr : 3103

**Applications** Used as initiator in co-polymerization of Ethylene, Styrene, Acrylonitrile, Vinyl Acetate, Acrylate and Metacrylates. Used during styrene co-polymerization at temperatures between 100 – 140 °C.

**Packaging** 25 kg PE Pail

**Handling & Storage** Must be kept between +8 C and +25 C. Keep pails tightly closed. Store and handle in a dry, well-ventilated place, away from sources of heat, ignition and direct sunlight in original packaging. Provide grounding and venting in order to prevent static electricity build-up. Avoid any contact with Amine and Cobalt Accelerators, acids, alkalis and heavy metal compounds such as driers and metal soaps.

**Shelf Life** 3 Months  
For unopened packages at recommended storage conditions

